

Product Specifications



Product	Product #	Sheen	Product Use	Vol Solids +/- 1.0%	Wt./Gal.	Hrs. Dry Re-Coat ¹	VOC g/L	Coverage ² Per Gal.
Waterlox ORIGINAL Formula								
Waterlox ORIGINAL Sealer/Finish	TB 5284	Medium	Sealer & Finish	22.3	6.95	24	614	500 Sq. Ft.
Waterlox ORIGINAL Satin Finish	TB 6044	Satin	Finish	33.6	7.28	24	524	500 Sq. Ft.
Waterlox ORIGINAL High Gloss Finish	TB 3182	High Gloss	Finish	34.1	7.18	24	523	500 Sq. Ft.
Waterlox ORIGINAL 350 VOC Sealer/Finish	TB 6038	Medium	Sealer & Finish	27.8	9.35	24	347	500 Sq. Ft.
Waterlox ORIGINAL 350 VOC Satin Finish	TB 6035	Satin	Finish	34.3	9.10	24	345	500 Sq. Ft.
Waterlox ORIGINAL 450 VOC Satin Finish	TB 6045	Satin	Finish	36.1	8.25	24	445	500 Sq. Ft.
Waterlox MARINE Formula								
Waterlox MARINE Sealer	TB 3809	Medium	Exterior Primer	22.3	6.95	24	614	500 Sq. Ft.
Waterlox MARINE Satin Finish	TB 6032	Satin	Exterior Finish	36.0	7.27	24	508	500 Sq. Ft.
Waterlox MARINE High Gloss Finish	TB 3940	High Gloss	Exterior Finish	43.6	7.44	24	450	500 Sq. Ft.
Waterlox TRUETONE Formula								
Waterlox TRUETONE Color-Infused Tung Oil Stains	Various	Matte/Flat	Sealer/Stain	70-75	7.58-8.77	24	< 275	3,200-3,400 Sq. Ft.
Waterlox TRUETONE Buff-In Tung Oil Finish	TB 7011	Matte/Flat	Finish	75.0	7.58	24	< 275	3,200-3,400 Sq. Ft.



¹ Based on adequate cross-ventilation, 70° F; and < 50% relative humidity. Review the Ventilation FAQs on our website at waterlox.com. ² Suggested spread rate(s). ³ After 12 hours must be sanded for inter-coat adhesion. ⁴ Must be buffed for inter-coat adhesion/aesthetics³ with a 3M Maroon pad

Product Specifications



Product	Product #	Sheen	Product Use	Vol Solids +/- 1.0%	Wt./Gal.	Hrs. Dry Re-Coat ¹	VOC g/L	Coverage ² Per Gal.
Waterlox URETHANE Formula								
Waterlox URETHANE Satin Finish	TB 5930	Satin	Finish	36.4	7.35	6 ³	527	500 Sq. Ft.
Waterlox URETHANE Gloss Finish	TB 4252	Gloss	Finish	34.0	7.22	6 ³	547	500 Sq. Ft.
Waterlox URETHANE Semi-Gloss Finish	TB 5824	Semi-Gloss	Finish	35.0	7.25	6 ³	541	500 Sq. Ft.
Waterlox H2OLOX Formula								
Waterlox H2OLOX Gloss Finish	TB 2000	Gloss	Finish	30.0	8.22	Overnight or minimum 16 hrs ⁴	188	500 Sq. Ft.
Waterlox H2OLOX Semi-Gloss Finish	TB 2003	Semi-Gloss	Finish	30.0	8.24	Overnight or minimum 16 hrs ⁴	184	500 Sq. Ft.
Waterlox H2OLOX Satin Finish	TB 2001	Satin	Finish	30.0	8.25	Overnight or minimum 16 hrs ⁴	185	500 Sq. Ft.
Waterlox H2OLOX Matte Finish	TB 2002	Matte	Finish	31.0	8.31	Overnight or minimum 16 hrs ⁴	188	500 Sq. Ft.
Waterlox UNIVERSAL Tung Oil Sealer								
UNIVERSAL Tung Oil Sealer (UTOS)	TB 1000	Flat	Sealer	87.0	7.77	Overnight or minimum 16 hrs ⁴	99	3200 Sq. Ft.
Waterlox Pure Tung Oil								
Waterlox Pure Tung Oil	TB 6050	Matte	Sealer & Finish	100.0	7.8	24+	0	4,000 Sq. Ft.



¹ Based on adequate cross-ventilation, 70° F; and < 50% relative humidity. Review the Ventilation FAQs on our website at waterlox.com. ² Suggested spread rate(s). ³ After 12 hours must be sanded for inter-coat adhesion. ⁴ Must be buffed for inter-coat adhesion/aesthetics* with a 3M Maroon pad